

UNCLASSIFIED

MASTER COPY

FOR REPRODUCTION PURPOSES

2

SECURITY CLASSIFICATION OF THIS PAGE

REPORT DOCUMENTATION PAGE				
1a. REP		1b. RESTRICTIVE MARKINGS		
2a. SEC		3. DISTRIBUTION/AVAILABILITY OF REPORT		
2b. DEI		Approved for public release; distribution unlimited.		
4. PERFORMING ORGANIZATION REPORT NUMBER(1)		5. MONITORING ORGANIZATION REPORT NUMBER(S)		
AD-A205 628		ARO 22677.11-LS		
5a. NAME OF PERFORMING ORGANIZATION Univ. of Connecticut		5b. OFFICE SYMBOL (If applicable)		7a. NAME OF MONITORING ORGANIZATION U. S. Army Research Office
6c. ADDRESS (City, State, and ZIP Code) Storrs, CT 06268		7b. ADDRESS (City, State, and ZIP Code) P. O. Box 12211 Research Triangle Park, NC 27709-2211		
8a. NAME OF FUNDING/SPONSORING ORGANIZATION U. S. Army Research Office		8b. OFFICE SYMBOL (If applicable)		9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER DAAG29-85-K-0222
8c. ADDRESS (City, State, and ZIP Code) P. O. Box 12211 Research Triangle Park, NC 27709-2211		10. SOURCE OF FUNDING NUMBERS		
		PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO.
		WORK UNIT ACCESSION NO.		
11. TITLE (Include Security Classification) The Mechanisms of Biodegradation of Synthetic Polymers				
12. PERSONAL AUTHOR(S) J. A. Cameron and S. J. Huang				
13a. TYPE OF REPORT Final		13b. TIME COVERED FROM 9/15/85 TO 12/31/88		14. DATE OF REPORT (Year, Month, Day) February 17, 1989
15. PAGE COUNT 5				
16. SUPPLEMENTARY NOTATION The view, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.				
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB-GROUP	Enzymes, Biodegradation, Polymers, Synthetic Polymers, Microbial Degradation	
19. ABSTRACT (Continue on reverse if necessary and identify by block number)				
<p>This research was an attempt to gain a better understanding of the processes involved in the microbial degradation of synthetic polymers. It involved the examination of extracellular and cell associated enzymes capable of cleaving the model polyester, polycaprolactone. An effort was made to compare these enzymes to gain some understanding of their multiplicity and activity. As information was gained regarding the degradation process we attempted the modification of other polymers to render them degradable or more degradable.</p>				
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION Unclassified	
22a. NAME OF RESPONSIBLE INDIVIDUAL			22b. TELEPHONE (Include Area Code)	22c. OFFICE SYMBOL

The Mechanisms of Biodegradation of Synthetic Polymers

Final Report

J.A. Cameron and S. J. Huang

February 17, 1989

U. S. Army Research Office

DAAG29-K-0222

The University of Connecticut

Approved for Public Release:

Distribution Unlimited

89 3 21 072

THE VIEW, OPINIONS, AND/OR FINDINGS CONTAINED IN THIS REPORT ARE THOSE OF THE AUTHORS AND SHOULD NOT BE CONSTRUED AS AN OFFICIAL DEPARTMENT OF THE ARMY POSISTION, POLICY, OR DECISION, UNLESS SO DESIGNATED BY OTHER DOCUMENTATION.

1. Forward - None
- 2 Table of Contents - None
3. Appendixes - None
4. A. Statement of the problem studied.

This research was an attempt to gain a better understanding of the processes involved in the microbial degradation of synthetic polymers. It involved the examination of extracellular and cell associated enzymes capable of cleaving the model polyester, polycaprolactone. An effort was made to compare these enzymes to gain some understanding of their multiplicity and activity. As information was gained regarding the degradation process we attempted the modification of other polymers to render them degradable or more degradable.

B. Summary of the most important results.

The majority of the work involved the yeast Cryptococcus laurentii, representing a single cell form of microbial degrader, and several members of the genus Fusarium, in particular Fusarium moniliforme, representing a filamentous organism involved in degradation. The extracellular enzyme of Cryptococcus laurentii was intensively studied. It has a high specific activity, a low molecular weight and is active over a relatively wide range of temperature and pH values. It is produced extracellularly in the late logarithmic stage of growth. The primary endproducts of its activity were trimers of caproic acid. While we were unable to demonstrate other proteins in our best extracellular enzyme preparations, we were unable to conclusively state that it was a pure preparation. The level of total protein was always very low when these organisms were grown in minimal medium, precluding assurance that some traces of other protein were not present following permeation chromatography. Even when the enzyme was concentrated by ultrafiltration, purified by gel permeation chromatography, and reconcentrated we could not verify purity because every method attempted led to a loss of enzyme activity. The enzyme apparently bound irreversibly to all of the ion exchange matrixes used as well as hydrophobic interaction media. When electrophoresis was attempted the enzyme activity was lost under all conditions. Earlier findings that a low molecular weight cofactor was necessary for enzyme activity were found to be spurious. We were unable to demonstrate any cell-associated enzyme by preparing protoplasts and looking for activity on the protoplast. The findings with Cryptococcus indicate that the organism is capable of elaborating significant amounts of hydrolytic enzyme which breaks the polymer down to a size that can be imbibed and utilized by the organism. This is the same pattern that we have seen in the bacterial genus Pseudomonas. Members of the genus Fusarium were found to vary considerably in their ability to degrade polycaprolactone but none of them elaborated large amounts of the enzyme, as judged by the size of the zone of clearing on polymer-agar plates. It was

A-1

found that Fusarium moniliforme, the most active organism on plates, produces only small amounts of enzyme extracellularly. When subjected to gel permeation chromatography three peaks of activity were seen. We are presently evaluating these peaks to determine whether the lower molecular weight ones are monomers of the largest one or whether they are independent enzymes. A preliminary attempt to electrophorese the preparations showed the same problem seen with the Cryptococcus enzyme, a loss of all activity. When protoplasts of Fusarium strains were prepared enzyme activity could be demonstrated in association with the protoplast. Holding the protoplasts in appropriate medium (proper salt and osmotic balance with nutrients to support metabolism) enzyme washed off the protoplasts and no more was produced, as they lost activity. Thus it appears that, in the organisms studied, two types of organisms are found, those that release relatively large amounts of efficient extracellular enzyme into their surroundings, and organisms that produce the enzyme in a periplasmic site, releasing relatively small amounts of it and retaining significant amounts in association with the cell.

We have also examined the effects of the modification of polymers on their biodegradability. The effect the catalyst used for polymer synthesis was examined for determination of their role in resistance or susceptibility to biodegradation. Para-toluene, tin chloride and zinc chloride were used as catalysts in the preparation of poly(hexamethylene tartrate) and poly(octamethylene tartrate) and their polyurethane derivatives. Para-toluene and tin chloride resulted in polymers that were susceptible to degradation by Aspergillus niger. On the other hand, the use of zinc chloride led to an inhibition of fungal degradation. This was apparently due to the release of zinc, which is known to be fungicidal and fungistatic, which had been entrapped in the polymer, and its action on the fungi as it was released into solution. The release was found to be linear with the square root of time. The effect of surface modification of aromatic polymers on their degradability was examined by treating polystyrene and poly(ethyleneterephthalate) (PET) with strong oxidizing agents. The polystyrene showed very little change but the PET showed marked surface changes, yielding a rough, irregular surface. These polymers did not, however, support growth of Fusarium moniliforme or other fungi any better than the original polymer. Heat treatment (120° C) and treatment with polyester depolymerase from Cryptococcus laurentii resulted in further surface changes, leading to the ability to support the growth of Fusarium. Enzyme treated surfaces were even more rough than untreated surfaces. Heated surfaces showed dramatic changes with a rough and convoluted form.

#### C. Publications

Cameron, J. A. and A. S. Costa 1987 Characterization of an extracellular polyester depolymerase of Cryptococcus laurentii. Biodeterioration Research 1. G. C. Llewellyn and C. E. O'Rear, Eds., Plenum Press, N. Y.. p.17

Cameron, J.A., C. L. Bunch and S. J. Huang, Microbial Degradation of Synthetic Polymers. Submitted to Biodeterioration 7. Proceedings of the Seventh International Biodeterioration Symposium.

Cameron, J.A., C.L. Bunch and S.J. Huang; Microbial Degradation of Synthetic Polymers. Accepted for publication in Biodeterioration 7.

Davis, P. A., L. Nicolais, L. Ambrosio and S. J. Huang 1987 Synthesis and Characterization of Semi-interpenetrating Networks of Poly(2-hydroxyethyl methacrylate) and Poly(caprolactone). Proc. P.M.S.E. Division, Am. Chem. Soc., 56, 536.

DiBenedetto, L. J., S. J. Huang and J. A. Cameron 1987 Biodegradation of Hydroxylated Polyurethanes. Proc. P.M.S.E. Division, Am. Chem. Soc., 57, 404.

Han, Y. K., P. G. Edelman and S. J. Huang Synthesis and Characterization of Crosslinked Polymers for Biomedical Composites. Submitted to J. Macromolec. Sci.: Chemistry.

Huang, S. J., P. G. Edelman and J. A. Cameron 1987 Crosslinkable Polyesters for Biomedical Composites (1). Advances in Biomedical Polymers. Ed. C.G. Gebelein. Plenum Publ. Corp. pp.101-109.

Mungai, V. W., J. A. Cameron, J. F. Johnson and S. J. Huang 1988 Surface Modification of Aromatic Polymers. Polym. Mat. Sci. Eng., 58, 610.

Ambrosio, L., G. Gaprino, L. Nicolais, L. Nicodemo, G. Guida, S. J. Huang and D. Ronca 1988 Composite Materials for Bone Fracture Fixation. Composite Structure 4, 2337.

Mungai, V. W., J. A. Cameron, J. F. Johnson and S. J. Huang 1988 Surface Modification of Aromatic Polymers. Polym. Mat. Sci. Eng., 58, 610.

DiBenedetto, L. J. and S. J. Huang 1988 Biodegradable hydroxylated polymers as controlled release agents. Polym. Mat. Sci. Eng. 29, 812-816.

DiBenedetto, L. J. and S. J. Huang Poly(alkylene tartrates) as biodegradable matrices for the controlled release of high and low molecular weight substances. Submitted to A. Chem. Soc. for publication in Proceedings of April 1989 national meeting.

#### C. Participating personnel.

J. A. Cameron, S. J. Huang, Laura J. DiBenedetto (PhD. Dec. 1989), Albert S. Costa (M. S. Dec. 1986), Lida Kimmel (M.S. 1989), Paul Urbanowski (M.S. 1988), Elizabeth Geiger.

5. Bibliography - None

6. Appendixes - None